

Tierrafino Lustro: Adhesion and covering capacity on different substrates

Substrate			Adhesion	Cover Cap.	Advice
Sheetrock/dry wall/plasterboard			****	****	
Sheetrock with gypsum plaster			****	*****	
Lime plaster			****	*****	
Concrete (smooth surface)			*****	****	
Aquapanel Knauf			*****	****	
Fermacell			*****	****	
YTONG			*****	***	
Bricks (baked clay)			***	***	
Masonite			*	***	Sandpaper
MDF			***	****	Sandpaper
Varnished wood (spruce)			*	**	Sandpaper
Untreated wood (sawn)			*****	***	
Triplex/multiplex (untreated)			*****	***	
Clay plaster finish			****	***	
Base clay coat			****	***	
Clay board			****	*	
Red Base clay			****	***	
Tadelakt			**	**	Sandpaper
Plastic			*	*	Sandpaper
Metal			*	*	Fix
Carton			****	***	
Latex			***	***	
wall paper			***	***	

Description of values of adhesion and covering capacity:

*	Very poor	2-3 coats Tierrafino Lustro	
**	Poor	2-3 coats Tierrafino Lustro	
***	Normal	2 coats Tierrafino Lustro	
****	Good	1-2 coats Tierrafino Lustro	
*****	Very good	1-2 coats Tierrafino Lustro	

These values concern untreated substrates.

After treatment with Tierrafino **Fix**, all substrates have approximately the same adhesion ******* and covering capacity *******.

Please note that covering capacity is related to the contrast in dark and light in the substrate and to the contrast between substrate and the colour of the applied ipaint. Dark substrates need more coats of white ipaint to cover than an equally white substrate. A light coloured substrate may need more coats ipaint Gomera grey than a dark substrate.

Although this product-description has been put together with utmost precision, Tierrafino will not be liable for any indirect or direct damage that may occur, by using the information offered in this product description.